

EAST Search History

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	4	(conduct\$3 same (powder particle fiber) same ratio same (mold\$3 extrud\$3 extrus\$3) same (capacitor lc) same fabric\$3).ab.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 12:17
L2	5	(conduct\$3 same (powder particle fiber) same (mold\$3 extrud\$3 extrus\$3) same (capacitor lc) same fabric\$3).ab.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 12:38
L3	90	(conduct\$3 same (powder particle fiber) same (mold\$3 extrud\$3 extrus\$3) same (capacitor lc)).ab.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 12:18
L4	7	3 & fabric\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 12:22
L5	33	3 and carbon\$3 and (form\$3 mold\$3 extrud\$3 extrus\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 12:54
L6	5	(conduct\$3 same (powder particle fiber resin) same (mold\$3 extrud\$3 extrus\$3) same (capacitor lc) same fabric\$3).ab.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 12:40
L7	309	(conduct\$3 same (powder particle fiber resin) same (mold\$3 extrud\$3 extrus\$3) same (capacitor lc)).ab.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 12:39
L8	2068	(conduct\$3 same (powder particle fiber resin) same (mold\$3 extrud\$3 extrus\$3 form\$3) same (capacitor lc)).ab.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 12:39

EAST Search History

L9	7	(conduct\$3 same (form\$3 powder particle fiber resin) same (mold\$3 extrud\$3 extrus\$3) same (capacitor lc) same fabric\$3).ab.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 12:41
L10	1546	8 & (layer plat\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 12:43
L11	9	10 and ((induct conduct\$3) with loop)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 12:44
L12	3	5 and method and mold\$3 and provid\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 13:10
L13	1159	(method with form\$3 with (lc resonator)).ab.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 13:11
L14	4	(method with form\$3 with (lc with resonator)).ab.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 13:13
L15	4	(method with (form\$3 mold\$3) with (lc with resonator)) and (resin fiber particle powder) and capacitor	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 13:17
L16	2	15 & (extrud\$3 extrus\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 13:19

EAST Search History

L17	72	((form\$3 mold\$3) with (lc with resonator)) and (resin fiber particle powder) and capacitor	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 13:18
L18	5	17 and (metal with powder)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 13:18
L19	3	17 & (extrud\$3 extrus\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/23 13:19